

RESIN PROPERTIES ⁽¹⁾

| | Method | Unit | Typical Value |
|----------------------|--------|-------------------|---------------|
| Melt Flow Index | D1238 | g/10 min | – |
| 190°C/2.16 kg | – | – | 0.07 |
| 190°C/21.6 kg (HLM1) | – | – | 8.0 |
| Density | D792 | g/cm ³ | 0.950 |
| Melting Temperature | D3418 | °F | 269 |

MECHANICAL PROPERTIES ^{(1) (2)}

| | Method | Unit | Typical Value |
|--|-----------|------|---------------|
| Tensile Strength at Yield | D638 | psi | 3,550 |
| Elongation at Break | D638 | % | >600 |
| 2% Flexural Modulus | D790 | psi | 140,000 |
| Oxidative-Induction Time 200°C | D3895 | min | >30 |
| Brittleness Temperature | D746 | °F | < -100 |
| Heat Deflection Temperature @ 66 psi | D648 | °F | 169 |
| Notched Constant Ligament Stress (600 psi) | F2136 | hr | >2000 |
| Strain Hardening Modulus | ISO 18488 | MPa | 70 |
| ESCR ⁽³⁾ 10% Igepal [®] , F10 | D1693, B | hr | >1000 |
| ESCR ⁽³⁾ 100% Igepal [®] , F10 | D1693, B | hr | >2000 |

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

(2) The data listed were determined on compression-molded specimens and may, therefore, vary from specimens taken from molded articles.

(3) Environmental Stress Crack Resistance (ESCR).

All tests were run under laboratory conditions using American Society for Testing and Materials standards (where applicable) or internal testing procedures. The data is offered in good faith but is intended as a general guide only, and does not necessarily represent results that may be obtained elsewhere. The use of Bayport Polymers LLC ("Baystar") products must be guided solely by the user's own methods for selection of proper formulation to ascertain fitness for any specific application. Baystar disclaims any responsibility for misuse or misapplication of its products and the user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained in the data or the use of the product. The data is provided without reference to any intellectual property issues, as well as federal, state, or local laws which may be encountered in the use thereof. BAYSTAR MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. Baystar's liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited, at customer option, to replacement of nonconforming goods or refund not to exceed the purchase price plus transportation charges thereon in respect to any material subject to a claim. In addition to any prohibitions of use (if any), Baystar may further prohibit or restrict the sale of its products into certain applications. For further information, please contact your Baystar representative. All products supplied by Baystar are subject to its standard terms and conditions set out in the contract or applicable purchase order. Baystar is a registered trademark of Bayport Polymers LLC. This document may not be distributed, displayed (in any form including a website), copied, altered, or reproduced in whole or in part without Baystar's prior written authorization. To the extent Baystar specifically authorizes distributing, displaying and/or copying this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information.

CHARACTERISTICS:

- Multimodal enhanced polyethylene resin made with Borstar[®] 3G Technology
- Excellent melt strength and extrusion processibility
- Superior slow crack growth resistance
- Robust thermal stability and durability
- Property booster for corrugated pipe

APPLICATIONS:

- Corrugated pipe
- Non-pressure pipe and conduit
- Profile extrusion / sheet
- Blow molding
- Meets AASHTO M294
- Meets material requirements for ASTM F2160

